ASME / ANSI B36.19 Stainless Steel Welded & Seamless Pipes Dimension in MM & Weight in KG/MTR

Nominal		Outside	Schedule 5 S		Schedule 10 S		Schedule 20 S		Schedule 40 S		Schedule 80 S		Schedule 160 S		xxs	
Pipe Size		Diameter														
			WT	WEIGHT	WT	WEIGHT	WT	WEIGHT	WT	WEIGHT	WT	WEIGHT	WT	WEIGHT	WT	WEIGHT
mm	inch	mm	mm	(KGM)	mm	(KGM)	mm	(KGM)	mm	(KGM)	mm	(KGM)	mm	(KGM)	mm	(KGM)
3	1/8	10.3	1.2	0.20	1.24	0.28	1.5	0.33	1.73	0.37	241	0.47	-	-	-	-
6	1/4	13.7	1.2	0.37	1.65	0.49	2.00	0.58	2.24	0.630	3.02	0.80	-	-	-	-
10	3/8	17.1	1.2	0.47	1.65	0.63	2.00	0.74	2.31	0.840	3.20	1.10	-	-	-	-
15	1/2	21.3	1.65	0.80	2.11	1.00	2.30	1.07	2.77	1.27	3.73	1.62	4.75	1.94	7.47	2.55
20	3/4	26.7	1.65	1.03	2.11	1.28	2.55	1.52	2.87	1.69	3.91	2.20	5.56	2.90	7.82	3.64
25	1	33.4	1.65	1.30	2.77	2.09	2.55	1.94	3.38	250	4.55	3.24	6.35	4.24	9.09	5.45
32	1.1/4	42.2	1.65	1.65	2.77	270	3.00	290	3.56	3.39	4.85	4.47	6.35	5.61	9.70	7.77
40	1.1/2	48.3	1.65	1.91	2.77	3.11	3.00	3.55	3.68	4.05	5.08	5.41	7.14	7.25	11.1	10.18
50	2	60.3	1.65	2.40	2.77	3.93	3.00	4.24	3.91	5.44	554	7.48	8.74	11.11	11.07	13.44
65	2.1/2	73.0	2.11	3.69	3.05	5.26	4.00	6.81	5.16	8.63	7.01	11.41	9.53	14.91	14.02	20.39
80	3	88.9	2.11	4.51	3.05	6.45	4.00	8.37	5.49	11.29	7.62	15.27	11.1	21.30	15.24	27.68
100	4	114.3	2.11	5.84	3.05	8.36	4.50	12.18	6.02	16.07	8.56	22.32	13.49	33.54	17.12	41.03
125	5	141.3	277	9.47	3.40	11.57	5.00	16.80	6.55	21.8	9.53	30.97	15.88	49.11	19.05	57.43
150	6	168.3	277	11.32	3.40	13.84	6.35	25.36	7.11	28.26	10.97	42.56	18.25	67.53	21.95	79.22
200	8	219.1	277	14.79	3.76	19.96	6.35	33.31	8.18	42.55	12.7	64.64	23.01	111.27	22.23	107.92
250	10	273.1	3.40	22.63	4.19	27.78	6.35	41.77	9.27	60.31	12.7	96.01	28.58	172.33	25.40	155.15
300	12	323.8	3.96	31.25	457	36.00	6.35	49.7	9.53	73.88	12.7	132.05	33.32	238.76	25.40	186.97
390	14	355.6	3.96	34.36	4.78	41.3	7.92	67.80	11.13	94.59						
400	16	406.4	4.19	41.56	4.78	47.29	7.92	77.83	127	123.30	ASTM A 312 TP 304					
450	18	457.2	4.19	46.81	4.78	53.26	7.92	87.71	14.27	155.80	ASTM A 312 TP 316L					
500	20	508.0	4.78	59.25	554	68.61	9.53	117.14	15.09	183.42	ASTM A 312 TP 317L					
600	24	610.0s	5.54s	82.47	6.35	94.45	9.53	141.12	17.48	255.41						